



ENDURER 620 GSM COTTON CANVAS

Properties	Specifications	Test Method	Test Standards
Composition	100% Cotton	N/A	
Consruction	3 Ply Plain weave	N/A	
Water Penetration (mm)			
<i>Hydraustatic Pressure Test</i>	180	mm	ISO 811
Weight (gsm)	620	gsm	ISO 3801
Width (cm)	160	cm	
Tensile Strength			
Warp	1550	Newton	ISO 13934-1
Weft	925	Newton	ISO 13934-1
Tear Strength			
Warp	60	Newton	AS2001.2.10
Weft	40	Newton	AS2001.2.10
Colour Fastness to Light			
<i>Xenon Arc Fading Lamp Test</i>	5+		ISO105-B02
Colour Fastness to Perspiration			
<i>Acid (change of colour shade)</i>	4-5		AATCC 15-2002
<i>Alkaline (change of colour shade)</i>	4-5		AATCC 15-2002
Colour Fastness to Rubbing			
<i>Staining of Transfer cloth</i>			
Dry	5		ISO 105-X12
Wet	4-5		ISO 105-X12
Colour Fastness to Water			
<i>Change of colour</i>	4-5		ISO-105-C06
Water Repellency	80	%	ISO 4920
Shrinkage			
Warp	2.0	%	ISO 7771
Weft	0.5	%	ISO 7771